

## OVERVIEW

Terragrout G33 is a flexible, quick setting ceramic tile grouting compound for interior and exterior use. Terragrout G33 is designed to fill joints up to 5mm in width. Terragrout G33 complies to the requirement as per EN 13888 and passes all tests required for CG2 classified grouts. Terragrout G33 is available in a range of attractive fade resistant colours.

## PROPERTIES

- Crack-free jointing
- Excellent adhesion
- Clear fade resistant colours
- Easy workability
- Quick setting
- Flexible

## AREAS OF USE

High strength coloured grout for use with tile joints <5mm, used with C2F adhesives where quick setting is required, used with S1/S2 adhesives where a flexible joint is required.

## PREPARATION OF SURFACE

Ensure that all tile joints and edges are free and clean of excess tile fixing mortar and foreign matter.

## MIXING

Add about 6 litres of water to 20kg of Terragrout G33 and mix thoroughly to a thick and creamy consistency. Let it stand for 5 minutes, re-stir and apply.

## APPLICATION & CLEANING OF TOOLS

Wait until the Terrafix has set (approx. 24 hours) before grouting. Apply Terragrout G33 diagonally into the joints with a rubber edged spatula. Remove excess grout with a moist sponge before drying. Do not apply Terragrout G33 to an area which is so large that it cannot be completed

within an hour. Porous tiles should be moistened with water before grouting. After Terragrout G33 has dried and before it has hardened, polish the tiles with a clean, dry cloth leaving the joints flush with the tile. 24 hours after grouting, moisten the joints with a wet sponge.

Clean tools and equipment with water after use.

## HEALTH & SAFETY

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant material safety data sheet.

## PACKAGING & STORAGE

Terragrout G33 is supplied powder form in 5kg and 20kg craft bags.

Store containers in a clean dry area protected from direct sunlight and extreme heat and cold. Unopened containers can be stored for 6 months. Use oldest material first.

TILE DIMENSIONS			MATERIAL CONSUMPTION RATE OF TERRAGROUT G33 ACCORDING TO JOINT WIDTH (kg/m <sup>2</sup> )						
LENGTH OF TILE (mm)	WIDTH OF TILE (mm)	THICKNESS OF TILE (mm)	JOINT WIDTH (mm)						
			2	3	4	5	10	15	20
50	50	4	0.5	0.8	1.0	1.3			
75	150	6		0.6	0.8	1.0	1.9	2.9	3.8
100	100	6		0.6	0.8	1.0	1.9	2.9	3.8
100	100	10		1.0	1.3	1.6	3.2	4.8	6.4
120	240	12		0.7	1.0	1.2	2.4	3.6	4.8
150	150	6		0.4	0.5	0.6	1.3	1.9	2.6
200	200	8		0.4	0.5	0.6	1.3	1.9	2.6
250	250	12		0.5	0.6	0.8	1.5	2.3	3.1
250	250	20		0.8	1.0	1.3	2.6	3.8	5.1
300	300	10		0.3	0.4	0.5	1.1	1.6	2.1
300	300	20		0.6	0.9	1.1	2.1	3.2	4.3
330	330	10		0.3	0.4	0.5	1.0	1.5	1.9
400	400	10		0.2	0.3	0.4	0.8	1.2	1.6
450	450	12			0.3	0.4	0.9	1.3	1.7
500	500	12			0.3	0.4	0.8	1.2	1.5
600	600	12			0.3	0.3	0.6	1.0	1.3

TERRACO offers a comprehensive range of products and services for most concrete and finishing needs. Please contact the TERRACO Technical Service Department or your local TERRACO agent for further information, samples, demonstrations and instructor services. The information given in this leaflet is based upon laboratory research, as well as extensive field work and application. All products are sold subject to standard conditions of sale which are available on request. This information is based on TERRACO's present state of knowledge and is intended to provide general information on TERRACO's products and their methods of use. The prospective user is recommended to determine the suitability of TERRACO's suggestions and products before adopting them on a commercial scale.

#### TECHNICAL DATA

<b>Product</b>	High strength, quick setting ceramic tile grout for joints up to 5mm.
<b>Binders</b>	Hydraulic/organic.
<b>Filler</b>	Crushed, precisely graded extenders.
<b>Additives</b>	Plasticizing agents, adhesion improving substances, as well as water retaining agents.
<b>Quality Type</b>	Passes tests as per CG2/EN13888.
<b>Colours</b>	Available in a fade resistant standard colour range.
<b>Application Temperature</b>	5-35°C
<b>Mixing Water %</b>	30%
<b>Pot Life</b>	20 minutes.
<b>Time to Finishing</b>	15 minutes.
<b>Ready for Light traffic Use</b>	3 hours.
<b>Ready for Use</b>	24 hours.
<b>Packaging</b>	Supplied in powder form in 5kg and 20kg craft bags.
<b>Storage</b>	6 months in original unopened containers.

For technical enquiries please contact your nearest Terraco representative:

#### CHINA:

**Terraco Architectural Coatings China Co., Ltd.**  
Tel: +86 (0)20 8759 4742  
Fax: +86 (0)20 8526 8056  
E-mail: sales@terraco.com.cn  
Web: www.terraco.com.cn

#### Terraco Chemical (Shanghai) Co., Ltd.

Tel: +86 (0)21 621020 48 / 18  
Fax: +86 (0)21 625205 47  
Email: sales@terraco.com.cn  
Web: www.terraco.com.cn

#### EGYPT:

#### Terraco Egypt Chemical Industries S.A.E.

Tel: +20 (0)22 29184 53 / 57 / 58  
Fax: +20 (0)22 29184 80  
E-mail: terraco@terraco.com.eg  
Web: www.terraco.com.eg

#### JORDAN:

#### Jordan Swedish Polymers Industrial Corp.

Tel: +962 (0)6 553 8751  
Fax: +962 (0)6 553 6560  
E-mail: terraco@nol.com.jo  
Web: www.terraco.jo

#### IRELAND:

#### Terraco Technical Centre, Ireland

Tel: +353 (0) 404 66555  
Fax: +353 (0) 404 66654  
E-mail: technical-centre@terraco.com  
Web: www.terraco.com

#### PAKISTAN:

**Terraco Pakistan Pvt. Ltd.**  
Tel: +92 (0)42 3529 70 56-8  
Fax: +92 (0)42 3529 70 55  
Email: terraco@terraco.pk  
Web: www.terraco.com

#### ROMANIA:

**Terraco Romania SRL**  
Tel: +40 (0)749 203 133  
Fax: +40 (0)318 148 810  
E-mail: ahaque@terraco.com  
Web: www.terraco.com

#### RUSSIA:

**OOO Terraco Sweden Ltd, Russia**  
Tel: +7 (0)495 9212 237  
Fax: +7 (0)495 6273 881  
E-mail: adm@terraco.ru  
Web: www.terraco.ru

#### OOO Terraco Vostok Ltd

Tel: +7 (0)4212 410563  
Fax: +7 (0)4212 410591  
E-mail: terracovostok@terrakovostok.ru  
Web: www.terraco.com

#### SOUTH KOREA:

**Terraco Korea Co., Ltd**  
Tel: +82 (0) 2 5611 551  
Fax: +82 (0)2 5671 771  
E-mail: terraco@terraco.co.kr  
Web: www.terraco.co.kr

#### THAILAND:

**Terraco Industry (Thailand) Limited**  
Tel: +66 (0)2 946 68 56 / 58  
Fax: +66 (0)2 946 68 59  
E-mail: terraco@terraco.co.th  
Web: www.terraco.com

#### TURKEY:

**Terraco Yapi Malzemeleri Sanayi Ve Ticaret AS**  
Tel: +90 (0)222 236 0423  
Fax: +90 (0)222 236 0425  
E-mail: terraco@terraco.com.tr  
Web: www.terraco.com.tr

#### UAE:

**Terraco UAE Ltd**  
Tel: +971 (0)4 326 2699  
Fax: +971 (0)4 326 2733  
E-mail: terraco@terraco.ae  
Web: www.terraco.com

#### UK:

**ADDAGRIP**  
Tel: +44 (0)1825 761 333  
Fax: +44 (0)1825 768 566  
E-mail: sales@addagrip.co.uk  
Web: www.addagrip.co.uk / www.terraco.com

#### VIETNAM:

**Terraco Vietnam Co., Ltd**  
Tel: +84 (0)650 3 820 100  
Fax: +84 (0)650 3 820101  
E-mail: terraco@terraco.com.vn  
Web: www.terraco.com



# TERRAGROUT G33

CG2 FLEXIBLE QUICK SETTING CERAMIC TILE GROUT  
FOR JOINTS UP TO 5mm

75825