

OVERVIEW

Styrobond DP is a basecoat and adhesive for the TERRACO EIFS Exterior insulating finishing system. It is easy to use by just adding water, improving on-site quality control. It shows excellent adhesion between substrate and expanded polystyrene boards when used as an adhesive. It also provides an excellent basecoat for embedding glass fibre mesh on top of which EIFS finishing coat is applied.

PRODUCT GRADES/CODES

Styrobond DP Grey	75410
Styrobond DP White	75410

PROPERTIES

- Water resistant
- Excellent adhesion
- Good flexural strength
- Good impact resistance
- Easy to use

AREA OF USE

Styrobond DP is used as an adhesive between mineral substrates and expanded polystyrene boards (EPS boards). Styrobond DP is used as an embedding mortar applied over EPS (expanded polystyrene), XPS (extruded polystyrene) and mineral wool panels to embed the glass fibre mesh prior to application of finish coats.

MIXING INSTRUCTIONS

Styrobond DP should be mixed on site with water in the ratio of approximately 4 parts Styrobond DP to 1 part water by weight, mixing with a high speed mixer for 3-5 minutes. Allow the material to stand for 10 minutes, remix and use. Mix only enough material for immediate use.

APPLICATION & CLEANING OF TOOLS

When used as an adhesive, apply to the EPS board and press into place using a level. Do not allow adhesive to skin before fixing in place.

When used as an embedding mortar, apply a coat of Styrobond DP mix to the EPS board and embed the mesh using a trowel. Apply another coat of mix to the surface to ensure full cover of the mesh and an overall thickness of approximately 3mm.

Clean tools and equipment with water after use.

HEALTH & SAFETY

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant material safety data sheet.

PACKAGING & STORAGE

Styrobond DP is supplied in 25kg paper sacks.

Store containers in a clean dry area protected from direct sunlight and extreme heat and cold. Unopened containers can be stored for 6 months. Use oldest material first.

TERRACO offers a comprehensive range of products and services for most concrete and finishing needs. Please contact the TERRACO Technical Service Department or your local TERRACO agent for further information, samples, demonstrations and instructor services. The information given in this leaflet is based upon laboratory research, as well as extensive field work and application. All products are sold subject to standard conditions of sale which are available on request. This information is based on TERRACO's present state of knowledge and is intended to provide general information on TERRACO's products and their methods of use. The prospective user is recommended to determine the suitability of TERRACO's suggestions and products before adopting them on a commercial scale.

TECHNICAL DATA

Product	EIFS Basecoat/Adhesive.
Composition	Mixture of cement minerals, organic binders and additives.
Appearance	Fine grey powder.
Mixing Ratio	By weight: 4:1 with water.
Density of Paste	1.7
Pot Life	3 hours at 25°C
Colours	Grey/white
Performance Tests	EOTA 004
Material Consumption	4-5kg/m ²
Packaging	25kg paper sacks.
Storage	6 months in original unopened container.

For technical enquiries please contact your nearest Terraco representative:

CHINA:

Terraco Architectural Coatings China Co., Ltd.
Tel: +86 (0)20 8759 4742
Fax: +86 (0)20 8526 8056
E-mail: sales@terraco.com.cn
Web: www.terraco.com.cn

Terraco Chemical (Shanghai) Co., Ltd.

Tel: +86 (0)21 621020 48 / 18
Fax: +86 (0)21 625205 47
Email: sales@terraco.com.cn
Web: www.terraco.com.cn

EGYPT:

Terraco Egypt Chemical Industries S.A.E.

Tel: +20 (0)22 29184 53 / 57 / 58
Fax: +20 (0)22 29184 80
E-mail: terraco@terraco.com.eg
Web: www.terraco.com.eg

JORDAN:

Jordan Swedish Polymers Industrial Corp.

Tel: +962 (0)6 553 8751
Fax: +962 (0)6 553 6560
E-mail: terraco@nol.com.jo
Web: www.terraco.jo

IRELAND:

Terraco Technical Centre, Ireland

Tel: +353 (0) 404 66555
Fax: +353 (0) 404 66654
E-mail: technical-centre@terraco.com
Web: www.terraco.com

PAKISTAN:

Terraco Pakistan Pvt. Ltd.

Tel: +92 (0)42 3529 70 56-8
Fax: +92 (0)42 3529 70 55
Email: terraco@terraco.pk
Web: www.terraco.com

ROMANIA:

Terraco Romania SRL

Tel: +40 (0)749 203 133
Fax: +40 (0)318 148 810
E-mail: ahaque@terraco.com
Web: www.terraco.com

RUSSIA:

OOO Terraco Sweden Ltd, Russia

Tel: +7 (0)495 9212 237
Fax: +7 (0)495 6273 881
E-mail: adm@terraco.ru
Web: www.terraco.ru

OOO Terraco Vostok Ltd

Tel: +7 (0)4212 410563
Fax: +7 (0)4212 410591
E-mail: terracovostok@terrakovostok.ru
Web: www.terraco.com

SOUTH KOREA:

Terraco Korea Co., Ltd

Tel: +82 (0) 2 5611 551
Fax: +82 (0)2 5671 771
E-mail: terraco@terraco.co.kr
Web: www.terraco.co.kr

THAILAND:

Terraco Industry (Thailand) Limited

Tel: +66 (0)2 946 68 56 / 58
Fax: +66 (0)2 946 68 59
E-mail: terraco@terraco.co.th
Web: www.terraco.com

TURKEY:

Terraco Yapi Malzemeleri Sanayi Ve Ticaret AS

Tel: +90 (0)222 236 0423
Fax: +90 (0)222 236 0425
E-mail: terraco@terraco.com.tr
Web: www.terraco.com.tr

UAE:

Terraco UAE Ltd

Tel: +971 (0)4 326 2699
Fax: +971 (0)4 326 2733
E-mail: terraco@terraco.ae
Web: www.terraco.com

UK:

ADDAGRIP

Tel: +44 (0)1825 761 333
Fax: +44 (0)1825 768 566
E-mail: sales@addagrip.co.uk
Web: www.addagrip.co.uk / www.terraco.com

VIETNAM:

Terraco Vietnam Co., Ltd

Tel: +84 (0)650 3 820 100
Fax: +84 (0)650 3 820 101
E-mail: terraco@terraco.com.vn
Web: www.terraco.com