

OVERVIEW

Terragrout G35 is a flexible, quick setting ceramic tile grouting compound for interior and exterior use. Terragrout G35 is designed to fill joints 4-20mm in width. Terragrout G35 complies to the requirement as per EN 13888 and passes all tests required for CG2 classified grouts. Terragrout G35 is available in a range of attractive fade resistant colours.

PROPERTIES

- Crack-free jointing
- Excellent adhesion
- Clear fade resistant colours
- Easy workability
- Quick setting
- Flexible

AREAS OF USE

High strength coloured grout for use with tile joints 4-20mm, used with C2F adhesives where quick setting is required, used with S1/S2 adhesives where a flexible joint is required.

PREPARATION OF SURFACE

Ensure that all tile joints and edges are free and clean of excess tile fixing mortar and foreign matter.

MIXING

Add about 4 litres of water to 20kg of Terragrout G35 and mix thoroughly to a thick and creamy consistency. Let it stand for 5 minutes, re-stir and apply.

APPLICATION & CLEANING OF TOOLS

Wait until the Terrafix has set (approx. 24 hours) before grouting. Apply Terragrout G35 diagonally into the joints with a rubber edged spatula. Remove excess grout with a moist sponge before drying. Do not apply Terragrout G35 to an area which is so large that it cannot be completed

within an hour. Porous tiles should be moistened with water before grouting. After Terragrout G35 has dried and before it has hardened, polish the tiles with a clean, dry cloth leaving the joints flush with the tile. 24 hours after grouting, moisten the joints with a wet sponge.

Clean tools and equipment with water after use.

HEALTH & SAFETY

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant material safety data sheet.

PACKAGING & STORAGE

Terragrout G35 is supplied powder form in 5kg and 20kg craft bags.

Store containers in a clean dry area protected from direct sunlight and extreme heat and cold. Unopened containers can be stored for 6 months. Use oldest material first.

TILE DIMENSIONS			MATERIAL CONSUMPTION RATE OF TERRAGROUT G35 ACCORDING TO JOINT WIDTH (kg/m ²)						
LENGTH OF TILE (mm)	WIDTH OF TILE (mm)	THICKNESS OF TILE (mm)	JOINT WIDTH (mm)						
			2	3	4	5	10	15	20
50	50	4	0.5	0.8	1.0	1.3			
75	150	6		0.6	0.8	1.0	1.9	2.9	3.8
100	100	6		0.6	0.8	1.0	1.9	2.9	3.8
100	100	10		1.0	1.3	1.6	3.2	4.8	6.4
120	240	12		0.7	1.0	1.2	2.4	3.6	4.8
150	150	6		0.4	0.5	0.6	1.3	1.9	2.6
200	200	8		0.4	0.5	0.6	1.3	1.9	2.6
250	250	12		0.5	0.6	0.8	1.5	2.3	3.1
250	250	20		0.8	1.0	1.3	2.6	3.8	5.1
300	300	10		0.3	0.4	0.5	1.1	1.6	2.1
300	300	20		0.6	0.9	1.1	2.1	3.2	4.3
330	330	10		0.3	0.4	0.5	1.0	1.5	1.9
400	400	10		0.2	0.3	0.4	0.8	1.2	1.6
450	450	12			0.3	0.4	0.9	1.3	1.7
500	500	12			0.3	0.4	0.8	1.2	1.5
600	600	12			0.3	0.3	0.6	1.0	1.3

TERRACO offers a comprehensive range of products and services for most concrete and finishing needs. Please contact the TERRACO Technical Service Department or your local TERRACO agent for further information, samples, demonstrations and instructor services. The information given in this leaflet is based upon laboratory research, as well as extensive field work and application. All products are sold subject to standard conditions of sale which are available on request. This information is based on TERRACO's present state of knowledge and is intended to provide general information on TERRACO's products and their methods of use. The prospective user is recommended to determine the suitability of TERRACO's suggestions and products before adopting them on a commercial scale.

TECHNICAL DATA

Product	High strength, quick setting ceramic tile grout for joints 4-20mm.
Binders	Hydraulic/organic.
Filler	Crushed, precisely graded extenders.
Additives	Plasticizing agents, adhesion improving substances, as well as water retaining agents.
Quality Type	Passes tests as per CG2/EN13888.
Colours	Available in a fade resistant standard colour range.
Application Temperature	5-35°C
Mixing Water %	20%
Pot Life	20 minutes.
Time to Finishing	15 minutes.
Ready for Light traffic Use	3 hours.
Ready for Use	24 hours.
Packaging	Supplied in powder form in 5kg and 20kg craft bags.
Storage	6 months in original unopened containers.

For technical enquiries please contact your nearest Terraco representative:

CHINA:

Terraco Architectural Coatings China Co., Ltd.
Tel: +86 (0)20 8759 4742
Fax: +86 (0)20 8526 8056
E-mail: sales@terraco.com.cn
Web: www.terraco.com.cn

Terraco Chemical (Shanghai) Co., Ltd.

Tel: +86 (0)21 621020 48 / 18
Fax: +86 (0)21 625205 47
Email: sales@terraco.com.cn
Web: www.terraco.com.cn

EGYPT:

Terraco Egypt Chemical Industries S.A.E.

Tel: +20 (0)22 29184 53 / 57 / 58
Fax: +20 (0)22 29184 80
E-mail: terraco@terraco.com.eg
Web: www.terraco.com.eg

JORDAN:

Jordan Swedish Polymers Industrial Corp.

Tel: +962 (0)6 553 8751
Fax: +962 (0)6 553 6560
E-mail: terraco@nol.com.jo
Web: www.terraco.jo

IRELAND:

Terraco Technical Centre, Ireland

Tel: +353 (0) 404 66555
Fax: +353 (0) 404 66654
E-mail: technical-centre@terraco.com
Web: www.terraco.com

PAKISTAN:

Terraco Pakistan Pvt. Ltd.
Tel: +92 (0)42 3529 70 56-8
Fax: +92 (0)42 3529 70 55
Email: terraco@terraco.pk
Web: www.terraco.com

ROMANIA:

Terraco Romania SRL
Tel: +40 (0)749 203 133
Fax: +40 (0)318 148 810
E-mail: ahaque@terraco.com
Web: www.terraco.com

RUSSIA:

OOO Terraco Sweden Ltd, Russia
Tel: +7 (0)495 9212 237
Fax: +7 (0)495 6273 881
E-mail: adm@terraco.ru
Web: www.terraco.ru

OOO Terraco Vostok Ltd

Tel: +7 (0)4212 410563
Fax: +7 (0)4212 410591
E-mail: terracovostok@terrakovostok.ru
Web: www.terraco.com

SOUTH KOREA:

Terraco Korea Co., Ltd
Tel: +82 (0) 2 5611 551
Fax: +82 (0)2 5671 771
E-mail: terraco@terraco.co.kr
Web: www.terraco.co.kr

THAILAND:

Terraco Industry (Thailand) Limited
Tel: +66 (0)2 946 68 56 / 58
Fax: +66 (0)2 946 68 59
E-mail: terraco@terraco.co.th
Web: www.terraco.com

TURKEY:

Terraco Yapi Malzemeleri Sanayi Ve Ticaret AS
Tel: +90 (0)222 236 0423
Fax: +90 (0)222 236 0425
E-mail: terraco@terraco.com.tr
Web: www.terraco.com.tr

UAE:

Terraco UAE Ltd
Tel: +971 (0)4 326 2699
Fax: +971 (0)4 326 2733
E-mail: terraco@terraco.ae
Web: www.terraco.com

UK:

ADDAGRIP
Tel: +44 (0)1825 761 333
Fax: +44 (0)1825 768 566
E-mail: sales@addagrip.co.uk
Web: www.addagrip.co.uk / www.terraco.com

VIETNAM:

Terraco Vietnam Co., Ltd
Tel: +84 (0)650 3 820 100
Fax: +84 (0)650 3 820101
E-mail: terraco@terraco.com.vn
Web: www.terraco.com