

OVERVIEW

Stucco Vintage G200 is a decorative mineral floor finish designed to give the appearance of a natural cast concrete floor. It is easy to apply and has excellent strength, abrasion resistance and durability. A range of attractive patterns can be achieved depending on application tools and installation method. It is finished with a clear resin based epoxy topcoat resulting in an attractive sheen which is easy to maintain.

PROPERTIES

Stucco Vintage G200 has the following properties:

- Faux concrete finish
- Easy to apply
- Excellent adhesion
- Excellent durability
- High abrasion resistance
- Low VOC system

AREAS OF USE

Stucco Vintage G200 is used for application on commercial floors such as offices, restaurants, shops and department stores.

PREPARATION OF SURFACE

Concrete floors should be fully cured for 3-4 weeks. Ensure that all dust, dirt and foreign matter are scraped and brushed away. All cracks, chips, voids and damages should be repaired first.

PRIMING

Apply a coat of P Primer Clear prior to application of Stucco Vintage G200. On extremely absorbent, porous surfaces or under extreme climatic conditions, apply 2 to 3 coats of primer

MIXING

Add powder to resin and mix using a drill agitator for 3 minutes until lump-free. Adjust viscosity with water to form a self leveling consistency.

Mixed material should be used within 1 hour of mixing. Do not re-temper material with extra water.

APPLICATION & CLEANING OF TOOLS

Stucco Vintage G200 is poured onto surface and spread with a smoothing trowel or spreader to the required thickness. Various patterns can be achieved using various application tool and method. Top coating should be applied after 72 hours.

Clean tools and equipment with water immediately after use.

HEALTH & SAFETY

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant material safety data sheet.

PACKAGING & STORAGE

Stucco Vintage G200 is supplied in 24kg plastic as a 2K system.

Store containers in a clean dry area protected from direct sunlight and extreme heat and cold. Unopened containers can be stored for 9 months. Use oldest material first.

TERRACO offers a comprehensive range of products and services for most concrete and finishing needs. Please contact the TERRACO Technical Service Department or your local TERRACO agent for further information, samples, demonstrations and instructor services. The information given in this leaflet is based upon laboratory research, as well as extensive field work and application. All products are sold subject to standard conditions of sale which are available on request. This information is based on TERRACO's present state of knowledge and is intended to provide general information on TERRACO's products and their methods of use. The prospective user is recommended to determine the suitability of TERRACO's suggestions and products before adopting them on a commercial scale.

TECHNICAL DATA

Product	Decorative mineral floor finish.
Binder	Hydraulic and organic binders.
Additives	Plasticizing agents, adhesion promoters and water retention agents.
Thickness of Layer	3-5 mm
Consumption	1.5 kg/m ² per 1mm thickness
Mixing Ratio	20 Kg powder/4 Kg resin
Compressive Strength	> 20 N/mm ²
Adhesion strength	> 1.08 N/mm ²
Length Change	±0.05 %
Packaging	24 kg plastic pails (20 Kg powder/4 Kg resin)
Storage	9 months in original unopened container.

For technical enquiries please contact your nearest Terraco representative:

ALGERIA:

SARL Terraco Algeria
Tel: +213 (0)23 23 07 80
Fax: +213 (0)23 23 07 80
E-mail: terraco@terraco.dz
Web: www.terraco.dz

IRELAND:

Terraco Technical Centre, Ireland
Tel: +353 (0) 1 2819 045
Fax: +353 (0) 1 2819 048
E-mail: technical-centre@terraco.com
Web: www.terraco.com

THAILAND:

Terraco Industry (Thailand) Limited
Tel: +66 (0)2 946 68 56 / 58
Fax: +66 (0)2 946 68 59
E-mail: terraco@terraco.co.th
Web: www.terraco.com

CHINA:

Terraco Architectural Coatings China Co., Ltd.
Tel: +86 (0)20 8759 4742
Fax: +86 (0)20 8526 8056
E-mail: sales@terraco.com.cn
Web: www.terraco.com.cn

PAKISTAN:

Terraco Pakistan Pvt. Ltd.
Tel: +92 (0)42 3529 70 56-8
Fax: +92 (0)42 3529 70 55
Email: terraco@terraco.pk
Web: www.terraco.com

TURKEY:

Terraco Yapi Malzemeleri Sanayi Ve Ticaret AS
Tel: +90 (0)222 236 0423
Fax: +90 (0)222 236 0425
E-mail: terraco@terraco.com.tr
Web: www.terraco.com.tr

Terraco Chemical (Shanghai) Co., Ltd.

Tel: +86 (0)21 621020 48 / 18
Fax: +86 (0)21 625205 47
Email: sales@terraco.com.cn
Web: www.terraco.com.cn

RUSSIA:

OOO Terraco Sweden Ltd, Russia
Tel: +7 (0)495 9212 237
Fax: +7 (0)495 6273 881
E-mail: adm@terraco.ru
Web: www.terraco.ru

UAE:

Terraco UAE Ltd
Tel: +971 (0)4 326 2699
Fax: +971 (0)4 326 2733
E-mail: terraco@terraco.ae
Web: www.terraco.com

EGYPT:

Terraco Egypt Chemical Industries S.A.E.
Tel: +20 (0)22 29184 53 / 57 / 58
Fax: +20 (0)22 29184 80
E-mail: terraco@terraco.com.eg
Web: www.terraco.com.eg

OOO Terraco Vostok Ltd

Tel: +7 (0)4212 410563
Fax: +7 (0)4212 410591
E-mail: terracovostok@terrakovostok.ru
Web: www.terraco.com

UK:

ADDAGRIP
Tel: +44 (0)1825 761 333
Fax: +44 (0)1825 768 566
E-mail: sales@addagrip.co.uk
Web: www.addagrip.co.uk / www.terraco.com

JORDAN:

Jordan Swedish Polymers Industrial Corp.
Tel: +962 (0)6 553 8751
Fax: +962 (0)6 553 6560
E-mail: terraco@nol.com.jo
Web: www.terraco.jo

SOUTH KOREA:

Terraco Korea Co., Ltd
Tel: +82 (0) 2 5611 551
Fax: +82 (0)2 5671 771
E-mail: terraco@terraco.co.kr
Web: www.terraco.co.kr

VIETNAM:

Terraco Vietnam Co., Ltd
Tel: +84 (0)650 3 820 100
Fax: +84 (0)650 3 820101
E-mail: terraco@terraco.com.vn
Web: www.terraco.com