

OVERVIEW

Terol is a range of superior quality, mineral based decorative renders designed for long-life protection of exterior facades and primarily used for finishing Terraco EIFS systems where it is top coated with Terracoat Stain. Terol is available in a range of decorative finishes and in a series of different grain sizes.

PRODUCT GRADES/CODES

Granule 1mm	71217
Granule 2mm	71133
Decor 2mm	71122
Decor 3mm	71214
Sahara 1mm	71215
Sahara 2mm	71216
Coarse	71120
Smooth	71110

PROPERTIES

Terol is formulated using a mixture of crushed and precisely graded laminar, inert extenders, special cements, limes and additives. This gives superior weather and pollution-resistant properties to the material, which has a life expectancy of more than 10 years, when applied correctly.

Decor

Terol Decor is a scratch finish coating, which is applied by steel trowel and patterned with a plastic trowel. It is available in 2mm and 3mm grain size.

Granule

Terol Granule is a high build, trowel applied coating, giving an even attractive granular finish. It is available in 1mm and 2mm grain sizes.

Sahara

Terol Sahara is a high build, trowel applied coating, giving a filled granular appearance. It is available in 1 mm and 2 mm arain sizes.

Coarse

Terol Coarse is a high build, coarse textured render, applied by spray or trowel.

Smooth

Terol Smooth is a low build, spray applied, even textured finish

AREA OF USE

Terol is primarily designed for exterior facades/surfaces of concrete, cement rendering, lightweight concrete, and fairfaced brickwork/blockwork, but is also usable on interior surfaces. Terol is ideal as a finish for Terraco EIFS (Exterior Insulating Finishing System).

PREPARATION OF SURFACE

Ensure all dust, dirt and foreign matter are brushed and scraped away. Also ensure surface is solid, free from salts, oil, grease and ridges. Protect all adjacent surfaces not to be coated. All surface defects should be repaired prior to application of Terol with Terramix/Styrobond DP.

MIXING PROPORTIONS

Terol is delivered in powder form and simply needs mixing with water using a high-speed mixer for approximately 1 minute, or a slow mixer for 5 minutes. For small quantities, mixing can be carried out with an agitator driven by a power drill.

APPLICATION & CLEANING OF TOOLS

Apply by trowel to a level granular finish. Do not apply moisture to trowel as this may cause discolouration.

Clean tools and equipment with water after use.

CURING

Allow the surface to air cure for 72 hours.

HEALTH & SAFETY

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant material safety data sheet.

PACKAGING & STORAGE

Product is supplied in 25kg plastic lined paper bags.

Store containers in a clean dry area protected from direct sunlight and extreme heat and cold. Unopened containers can be stored for 6 months. Use oldest material first.



Mineral based decorative coating.	
Available in 16 standard colours.	
Crushed, precisely graded extenders.	
Blend of special cements, lime and organic binders.	
Plasticizers, water-retention and adhesion-improving additives.	
+10 years.	
25kg double - walled laminated bags.	
6 months in original unopened containers.	

Grade	Grain Size	Consumption Rate (Kg / m2)	Water Demand per 25kg bag
Terol Granule	1mm	3-4	4.5-5.5
	2mm	4-5	4.5-5.5
Terol Decor	2mm	3-4	4.5-5.5
	3mm	7-5	4.5-5.5
Terol Sahara	1mm	3-4	4.5-5.5
	2mm	4-5	4.5-5.5
Terol Coarse	-	6-7	5.0-5.5
Terol Smooth	-	2-3	5.75-6.25

TERRACO offers a comprehensive range of products and services for most concrete and finishing needs. Please contact the TERRACO Technical Service Department or your local TERRACO agent for further information, samples, demonstrations and instructor services. The information given in this leaflet is based upon laboratory research, as well as extensive field work and application. All products are sold subject to standard conditions of sale which are available on request. This information is based on TERRACO's present state of knowledge and is intended to provide general information on TERRACO's products and their methods of use. The prospective user is recommended to determine the suitability of TERRACO's suggestions and products before adopting them on a commercial scale.



For technical enquiries please contact your nearest Terraco representative:

CHINA:

Terraco Architectural Coatings China Co., Ltd. Tel: +86 (0)20 8759 4742 Fax: +86 (0)20 8526 8056 E-mail: sales@terraco.com.cn

Web: www.terraco.com.cn

Terraco Chemical (Shanghai) Co., Ltd. Tel: +86 (0)21 621020 48 / 18 Fax: +86 (0)21 625205 47 Email: sales@terraco.com.cn Web: www.terraco.com.cn

EGYPT:

Terraco Egypt Chemical Industries S.A.E.

Tel: +20 (0)22 29184 53 / 57 / 58 Fax: +20 (0)22 29184 80 E-mail: terraco@terraco.com.eg Web: www.terraco.com.eg

JORDAN:

Jordan Swedish Polymers Industrial Corp.

Tel: +962 (0)6 553 8751 Fax: +962 (0)6 553 6560 E-mail: terraco@nol.com.jo Web: www.terraco.jo

IRELAND:

Terraco Technical Centre, Ireland

Tel: +353 (0) 404 66555 Fax: +353 (0) 404 66654

E-mail: technical-centre@terraco.com

Web: www.terraco.com

PAKISTAN:

Terraco Pakistan Pvt. Ltd.

Tel: +92 (0)42 3529 70 56-8 Fax: +92 (0)42 3529 70 55 Email: terraco@terraco.pk Web: www.terraco.com

ROMANIA:

Terraco Romania SRL

Tel: +40 (0)749 203 133 Fax: +40 (0)318 148 810 E-mail: ahaque@terraco.com Web: www.terraco.com

RUSSIA:

OOO Terraco Sweden Ltd, Russia

Tel: +7 (0)495 9212 237 Fax: +7 (0)495 6273 881 E-mail: adm@terraco.ru Web: www.terraco.ru

OOO Terraco Vostok Ltd

Tel: +7 (0)4212 410563 Fax: +7 (0)4212 410591

E-mail: terracovostok@terracokhv.ru

Web: www.terraco.com

SOUTH KOREA:

Terraco Korea Co., Ltd

Tel: +82 (0) 2 5611 551 Fax: +82 (0)2 5671 771 E-mail: terraco@terraco.co.kr Web: www.terraco.co.kr

THAILAND:

Terraco Industry (Thailand) Limited

Tel: +66 (0)2 946 68 56 / 58 Fax: +66 (0)2 946 68 59 E-mail: terraco@terraco.co.th Web: www.terraco.com

TURKEY:

Terraco Yapi Malzemeleri Sanayi Ve Ticaret AS

Tel: +90 (0)222 236 0423 Fax: +90 (0)222 236 0425 E-mail: terraco@terraco.com.tr Web: www.terraco.com.tr

UAE:

Terraco UAE Ltd

Tel: +971 (0)4 326 2699 Fax: +971 (0)4 326 2733 E-mail: terraco@terraco.ae Web: www.terraco.com

UK:

ADDAGRIP

Tel: +44 (0) 1825 761 333 Fax: +44 (0) 1825 768 566 E-mail: sales@addagrip.co.uk

Web: www.addagrip.co.uk / www,terraco.com

VIETNAM:

Terraco Vietnam Co., Ltd

Tel: +84 (0)650 3 820 100 Fax: +84 (0)650 3 820101 E-mail: terraco@terraco.com.vn Web: www.terraco.com